

Product Data


Nox-Rust® 3100G Rust Preventive Liquid

Description

Nox-Rust 3100G is a solvent cutback corrosion preventive compound. The dry film is amber color, and translucent. The thixotropic nature of Nox-Rust 3100G is capable of building high films. It clings to metals without dripping. Designed for use on ferrous and non-ferrous metals when exposed to indoor or outdoor storage conditions.

Used as a transit coating, it protects metal and most painted surfaces during domestic and international shipment. Excellent humidity and salt spray protection properties. Ideal for protecting equipment and machinery during export and outdoor environments..

Features



Proven Daubert Cromwell corrosion inhibitor chemistry

- Protects ferrous and non-ferrous metals
- Clings to metal surfaces
- Dry to the touch in 2-4 hours. Cures in 24 hours.
- Dried film is non-tacky, amber colored, wax-like and semi-transparent
- OEM Approved
- Compatible with Daubert Cromwell corrosion inhibitor papers, films and emitters
- Available in 5-gal drums, 55-gal. drums and totes.

Typical Applications



Transport, export, storage of metal products

- Hose fittings, connectors, and similar exposed areas
- Equipment, machinery, and components during overseas shipments
- Large metal parts stored outdoors
- Long-term indoor storage of metal parts, dies, tools, spares
- Castings and machined surfaces that cannot be protected from the elements
- Fabricated metal components and sub-assemblies

Surface Preparation and Application:

The metal surface should be clean, dry and free of rust, oil and mil scale. Metal temperature should be between 50-95°F (10-35°C) at the time of application. Apply by dip, brush or spray. Apply Nox-Rust 3100G 8-10 mils wet. The dry thickness will be 3.6-4.5 mils. Buildup of more than 6 mil is undesirable and not required.

When using an airless spray system, recommended equipment is a 15:1 or 23:1 type pump, a regulator, 25- or 50-ft. hose, and a P-500 type spray gun with a reversible tip. Tip size could range 319-.321. Spray pressure is typically between 65-80 psi. Recommended starting point is 70 psi, and then adjust as operator determines is best for the application.

The curing process takes place by solvent evaporation. Allow adequate ventilation. Dry time will be affected by temperature and humidity. Typical dry-to-handle time is 2-4 hours, curing in 24 hours. The coating will have self-healing properties for up to 90 days.

Removal

Nox-Rust 3100G liquid can be removed from metal surfaces by most solvent borne thinners , by vapor degreasing , high press ure hot alkaline wash, low pressure steam or using mineral spirits or kerosene –soaked towels.



DAUBERT CROMWELL
The Leading Name in Corrosion Prevention®

12701 S. Ridgeway Ave | Alsip, IL 60803 USA | (800) 535-3535

Tel +1 (708) 293-7750 | E-mail: info@daubertcromwell.com | www.daubertcromwell.com



Technical Data

Nox-Rust 3100G

Rust Preventive Liquid

Physical Data

Physical Properties	Typical Values
Color	Amber
Application	Dip, spray or brush
Recommended dry film thickness over metal profile	4 mils
Theoretical coverage @ recommended DFT	180 ft ² /gal (4.4 m ² /l)
Removal	Hot pressurized steam with hot alkaline soap, vapor degreasing, mineral spirits.
Film Type	Non-tacky, wax-like, semi-transparent
Specific Gravity @ 60°F (15.6°C)	0.89
Density, Weight per Gallon @ 77°F (25°C)	7.4 lbs./gallon
Flash Point (Penske Martin Closed Cup)	106°F
Percent Solids by Weight	54
Viscosity	25000cp
VOC content, max	3.5 lbs./gallon
High temperature flow point, minimum	300°F
Protective Properties	
5% Salt Spray (ASTM-B-117)	1,512 Hours (Min.)
100% Relative Humidity (ASTM-D-1748 @recommended DFT))	2,000 Hours (Min.)
Cure time	24 hours
Indoor Storage	5 years (Min.)

Approvals

RoHS compliant, OEM approved.

Storage

Store at temperatures between 50-95°F (10-35°C). Mild agitation is recommended prior to use. Material may thicken if stored below room temperature. Warm back to room temperature before use.

Shelf Life

12 months from date of shipping, stored in the original shipping container used by Daubert Cromwell and not in high humidity and not at high temperatures, or stored outside. Store unused VCI liquid in a cool, dry place, away from direct sunlight. Storage outside these conditions voids this statement.

Note

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus adversely affecting the performance of this coating. If a product other than Daubert Cromwell's recommended product is required, written authorization must be obtained from Daubert Cromwell.

WARRANTY The data, statements and recommendations in this product specification sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use. All products manufactured by us are warranted to be first class material and free from defects in material and

workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products. We make no warranty, express or implied, as to the suitability of any of our products for any particular use, and we shall not be subject to liability from any damages resulting from their use in operations not under our direct control. This warranty is exclusive of all other warranties, express or implied, and no representative of ours or any other person is authorized to assume for us any other liability in connection with the sale of our products.